# **JET-PLEX-EP** ™ LITHIUM COMPLEX GREASE



#### DESCRIPTION

JET-PLEX-EP™ Lithium Complex Grease is the ideal multipurpose grease for use in extreme pressure and high temperature operating conditions. It is the top of the line product for severe applications and general purpose lubricant.

JET-PLEX-EP is manufactured from carefully selected petroleum oils and lithium complex soap to create a multipurpose grease with a dropping point of 550°F (288°C). It has a smooth texture with a heavy body consistency, but provides good pumpability in both hot and cold operating temperatures. JET-PLEX-EP has excellent resistance to water and water washout problems. Oil separation is minimal even under extreme pressure. Heat cycling produces only a minor change in consistency. JET-PLEX-EP is formulated with special lubricity, anti-wear, and extreme pressure additives and fortified with rust, corrosion and oxidation inhibitors.

- Lithium complex base
- Excellent for high temperatures, high load applications--will not run or pound out
- Pumpable both hot or cold
- · Extremely resistant to rust and oxidation
- Smooth in texture
- Color–Red typical
- Available in NLGI "1" and "2" grades

### **APPLICATIONS**

**JET-PLEX-EP** is recommended for all types of bearing and sliding applications, for shock-loading, pounding, rough chassis usage and high loads. **JET-PLEX-EP** is the multipurpose lubricant that can replace several conventional type greases, resulting in smaller required inventories and less chance of misapplication.

#### PRODUCT CHARACTERISTICS

Thickener	Lithium Compley
	Lithium Complex Petroleum Oil
Fluid Type	Red
Color/Appearance	
Dropping Point (ASTM D-2265)	>550°F (288°C)
Specific Gravity	0.91
Density (lbs./gal.)	7.6
Additive Type	Organic EP/AW & R&O
Flash Point (ASTM D-92)	>430°F (221°C)
Autoignition Point (Calculated)	>500°F (260°C)
NLGI Grades	1 & 2
Copper Strip Corrosion	1A
(ASTM D-4048)	
4-Ball (ASTM D-2596)	
Weld Point, kgf	315
Load Wear Index	38
Wear Scar Diameter (ASTM D-2266)	0.45
Oxidation Resistance (ASTM D-942)	
PSI Drop, 100 hours	<5.0
Base Oil Viscosity (ASTM D-445)	
cSt @ 40°C	140 - 200
Wheel Bearing Life Performance	180 hrs. typ.
(ASTM D-3527)	

#### PACKAGING

Code No.	<b>Container Size</b>	Container
31750	14 oz.	Cartridge
31705	1 lb.	Can
31706	5 lb.	Can
31716	35 lb.	Pail
31724	120 lb.	Drum
31729	400 lb.	Drum

#### LIMITED WARRANTY

Jet-Lube, Inc. makes the Limited Express Warranty that at the date of delivery, this product shall be free from defects in Jet-Lube, Inc. materials and workmanship.

This Limited Express Warranty is expressly in lieu of any other express or implied warranties, including any implied warranty of merchantability or fitness for a particular purpose, and of any other obligation on the part of Jet-Lube, Inc.

The sole remedy for breach of the Limited Express Warranty shall be the refund of the purchase price. All other liability is negated and disclaimed, and Jet-Lube, Inc. shall not be liable for incidental or consequential damages.

## **AUTHORISED DISTRIBUTOR**

**JET SEALANTS & LUBRICANTS** 

+91-22-24130003 info@jetsealants.in www.jetsealants.in